



A beautifully soft hide which is suitable for use in luxury VIP environments.

## Application Usage

- |  |   |   |  |  |
|--|---|---|--|--|
| <input type="checkbox"/> Light Domestic              | <input type="checkbox"/> Light Contract (Crib 5)              | <input type="checkbox"/> General Marine | <input checked="" type="checkbox"/> General Aviation   | <input type="checkbox"/> After Market Auto |
| <input checked="" type="checkbox"/> General Domestic | <input checked="" type="checkbox"/> General Contract (Crib 5) | <input type="checkbox"/> Luxury Marine  | <input checked="" type="checkbox"/> Corporate Aviation | <input type="checkbox"/> Luxury AM Auto    |
| <input type="checkbox"/> Heavy Domestic              | <input type="checkbox"/> Heavy Contract (Crib 5)              |   | <input type="checkbox"/> Aviation Panels               | <input type="checkbox"/> OEM Std Auto      |
|  | <input type="checkbox"/> Severe Contract (Crib 7)             |   |  | <input type="checkbox"/> OEM Luxury Auto   |

## Test Results

Test	Method	Requirement
Substance	BS EN ISO 2589:2002	0.9 - 1.0mm
Fastness to Light	BS EN ISO 105-BO2:1999	Min 5 Blue Scale
Fastness to Rubbing	BS EN 11640/11641:1998	250 Wet/500 Dry
Flex Endurance	BS EN 5402:2002	50,000
Tear Strength	BS EN 3377-1:2002	40N
Finish Adhesion	ISO 11644:1993	4N
pH (min)	EN ISO 4045:1998	Min 3.2
Water Spotting	ISO 15700:1999	Grade 3 (No Residual Halo)
Cold Crack	EN ISO 17233:2002	-15C
Domestic FR	BS 8582:1979	Pass
Contract FR	BS 7176 - Crib 5	Pass
Aviation FR	JAR 25.853 a (app F) 1.(1).1	Pass